Visualize a published system sheet

FNP system

FNP number : 1112

Index FNP : S002

Last publication : 2022/05/16

State : PUBLISHED

Supplier : MAX PERLES

Total thickness : 2600 µm

public comment EN : June 24th, 2021 : First publication of the coating system. The resistance to liquids representative of the effluents resulting from the Steam Generators chemical cleaning processes has been demonstrated by tests carried out within the Corrosion Institute of Saint-Etienne and within the DI / TEGG laboratory. ***** Warning ***** Any intervention on the product once applied (sanding, grinding, etc.) can emit respirable silica dust : wear a P3 mask !

Utilities type : PARC NUCLEAIRE

Codifications published

Série	Groupe
PLF PLG PLH PLJ	308

Coat list

Coat number	Product name	Thickness	Nature of the binder	Type of phase	Proportion of solvent
1	ELECTROPERL	1600 µm	Epoxy polyamine	SS	
2	MAT 450		Renfort		
3	ELECTROPERL		Epoxy polyamine	SS	
4	REVÊTEMENT AR 100/MD9	1000 µm	Epoxy polyamine	SS	
5	-=-=-=-=-=-=-=-=-=				
6	SILICE F15				