Visualize a published system sheet

FNP system

FNP number : 1134

Index FNP : S002

Last publication : 2024/09/17

State : PUBLISHED

Supplier : RESIPOLY CHRYSOR

Total thickness : 975 µm

public comment EN : June 2nd, 2023 : First publication of the system *****WARNING***** The product NOVASSOL EPU-R is classified CMR2 according to the European Union CLP regulation. In order to apply this product safely, it is necessary to carry out a risk analysis and to put in place suitable collective and individual protections. *****WARNING***** In the case of sanding and / or grinding after hardening of the product NOVASSOL EPU or NOVASSOL EPU-R loaded with silica sand HN38, respirable silica dust may be emitted: wear a P3 mask ! The architecture reproduced in the list of layers is one of the possible options offered by the technical datasheet: - Depending on the desired reactivity, NOVASSOL EPU-R can be used instead of NOVASSOL EPU. - Depending on the state of the support, when the substarte is very open and/or very porous, the layer of NOVASSOL EPU (or NOVASSOL EPU-R) is loaded with HN38 silica sand.

Utilities type : PARC NUCLEAIRE

Technical sheet : FT FNP1134_ENG_Nov 2022.pdf

Codifications published

Série	Groupe
PLB/ELB PLE/ELE PLF/ELF PLG/ELG PLH/ELH PLJ/ELJ	349

Coat list

Coat number	Product name	Thickness	Nature of the binder	Type of phase	Proportion of solvent
1	NOVASSOL EPU	200 g/m²	EPOXY	SV	0.5
2	NOVAFILL EP 23 D	400 g/m²	EPOXY	SV	0.7
3	NOVADUR 1060 T	550 µm	EPOXY	SV	1
4	-=-=-=-=-=-=-=-=-=				
5	NOVASSOL EPU-R	Version plus réactive	EPOXY	SV	0.5
6	SABLE SILICEUX HN 38	Charges			
7	RESISOLV E	Solvant (nettoyage des outils)			
8	DILUANT PU41				