# Visualize a published system sheet

## FNP system

**FNP number :** 1135

**Index FNP :** S002

**Last publication :** 2024/09/17

**State :** PUBLISHED

**Supplier :** RESIPOLY CHRYSOR

**Total thickness :** 1525 µm

**public comment EN :** June 2nd, 2023 : First publication of the system *****WARNING***** The product NOVASSOL EPU-R is classified CMR2 according to the European Union CLP regulation. In order to apply this product safely, it is necessary to carry out a risk analysis and to put in place suitable collective and individual protections. *****WARNING***** In the case of sanding and / or grinding after hardening of the product NOVASSOL EPU or NOVASSOL EPU-R loaded with silica sand HN38, respirable silica dust may be emitted: wear a P3 mask ! The architecture reproduced in the list of layers is one of the possible options offered by the technical datasheet: - Depending on the desired reactivity, NOVASSOL EPU-R can be used instead of NOVASSOL EPU. - Depending on the state of the support, when the substarte is very open and/or very porous, the layer of NOVASSOL EPU (or NOVASSOL EPU-R) is loaded with HN38 silica sand.

**Utilities type :** PARC NUCLEAIRE

**Technical sheet :** FT FNP1135_ENG_nov 2022.pdf

## Codifications published

| Série | Groupe |
|---|---|
| PLA/ELA PLB/ELB PLD/ELD PLE/ELE PLF/ELF | 350 |

## Coat list

| Coat number | Product name | Thickness | Nature of the binder | Type of phase | Proportion of solvent |
|---|---|---|---|---|---|
| 1 | NOVASSOL EPU | 200 g/m² | EPOXY | SV | 0.5 |
| 2 | NOVAFILL EP 23 D | 400 g/m² | EPOXY | SV | 0.7 |
| 3 | NOVADUR 1060 T | 1100 µm | EPOXY | SV | 1 |
| 4 | -=-=-=-=-=-=-=-=-= | | | | |
| 5 | NOVASSOL EPU-R | Version plus réactive | EPOXY | SV | 0.5 |
| 6 | SABLE SILICEUX HN 38 | Charges | | | |
| 7 | RESISOLV E | Solvant (nettoyage des outils) | | | |
| 8 | DILUANT PU41 | | | | |