Visualize a published system sheet

FNP system

FNP number : 325

Index FNP : S005

Last publication : 2024/03/14

State : PUBLISHED

Supplier : MAX PERLES

Total thickness : 3.0 MM

public comment EN : Nov 3rd, 2023: the multifunction primer “Impression W” is renamed “Impression W1” following solvent reformulation. The DI/TEGG note ref. D309520005752 validated the qualification maintaining of all the FNP systems concerned. It should also be noted that the trade name of "Impression W1" at international level is "Primer W1" and that there is no difference of any kind between these two primers. Finally, the Render EDO is deleted from FT n°0 from its revision 12: in practice, it has not been used for years. Render AR100 is preferred, which is also qualified and fulfills the same functions, whether for heavy leveling or for fine raking. April 27th, 2022: the DI/TEGG note ref. D309522008936 validates the extension of the FNP 1007 qualification scope to the PLJ 349 codification. Dec. 12th, 2019 : ***** Warning ***** Any intervention on the product once applied (sanding, grinding, etc.) can emit respirable silica dust : wear a P3 mask ! CE SYSTEME A SUBI AVEC SUCCES L'ESSAI SEQUENTIEL (APRP APRES IRRADIATION) CE SYSTEME EST LE SEUL SYSTEME QUALIFIE POUR LES PUISARDS RIS EAS SUR SUPPORT BETON UNIQUEMENT AVEC MAT M4 ET TISSU P45 (FICHE TECHNIQUE 325A) VARIANTE AVEC 1 SEUL TISSU P80-800G/M2 (FICHE TECHNIQUE 325 B) RENFORCE AVEC 1 SEUL TISSU P120 DE 1200G/M2.(FICHE TECHNIQUE 325 C) FICHE TECHNIQUE N°0 INDICE 01 EN DATE DU 11/03/2011 ANNEXEE A LA FICHE 325 . 04/05/2018 : Mise à jour de la FT - Suppression des codifications PLG/ELG et PLL/ELL

Utilities type : PARC NUCLEAIRE

Technical sheet : FT FNP325 ENG.pdf

Codifications published

Série	Groupe
PLA/ELA PLB/ELB PLD/ELD PLE/ELE PLF/ELF PLH/ELH PLJ/ELJ	351

Coat list

Coat number	Product name	Thickness	Nature of the binder	Type of phase	Proportion of solvent
12	SILICE F15				
1	PRIMAIRE EDO	250.0 g/m²	Epoxy polyamide	AQ	53
2	ENDUIT AR100		Epoxy polyamine	SS	
3	ELECTROPERL	1000 + 800 g/m²	Epoxy polyamine	SS	
4	MAT 450 +TISSU DE VERRE P45	450 + 450 g/m²	Armature en fibres de verre		
5	ELECTROPERL	700 g/m²	Epoxy polyamine	SS	
6	ELECTROPERL	900 g/m²	EPOXY POLYAMINE	SS	
7	-=-=-=-=-=-=-=-=-=				
8	TISSU DE VERRE P80	800g/m²	Armature de verre (variante)	SS	
9	TISSU DE VERRE P120	1200g/m²	Armature de verre (renforcée)	SS	
10	IMPRESSION W1		Primaire polyvalent	SV	28
11	DILUANT ED				