

Visualize a published system sheet

FNP system

FNP number : 1160

Index FNP : S002

Last publication : 16/07/2025

State : PUBLISHED

Supplier : GEHOLIT

Total thickness : 220 µm

public comment EN : PEX coating (suitable in CX corrosivity atmosphere according to ISO 12944-2) that is applied on galvanised steel and with decontaminable fonction. Provided from ACQPA system CX H GNV 884.. /!\ Classification of reaction to fire : D-s1, D0 acc. to NF EN 13501-1+A1.

intern comment : Première importation du système CX H GNV 884 de l'ACQPA.

Utilities type : PARC NUCLEAIRE

Technical sheet : [FT EN 1160 Rev 5 Juin 2025.pdf](#)

Codifications published

Série	Groupe
PED PEX	231
PED PEX	220

Coat list

Coat number	Product name	Thickness	Nature of the binder	Type of phase	Proportion of solvent
1	GEHOTEX W91	120 µm	Acrylique	SV	38.5
2	WIEREGEN M25	100 µm	Polyuréthane	SV	29
3	-----				
4	VERDUNNUNG V-89				