Visualize a published system sheet

FNP system

FNP number : 1147

Index FNP : S007

Last publication : 2025/10/22

State : PUBLISHED

Supplier : MAX PERLES

Total thickness : 3 mm

public comment EN : May 20th, 2022: Publication of the Technical Data Sheet for FNP 1147 coating system targeting codification PLK352 - airtightness coating of the intrados of Reactor Building Internal Enclosure (PWR French Fleet)

Utilities type : PARC NUCLEAIRE

Codifications published

Série	Groupe
PLK	352

Coat list

Coat number	Product name	Thickness	Nature of the binder	Type of phase	Proportion of solvent
1	VERNIS ED1	30 µm	Epoxy polyamide	SV	54
2	PRIMAIRE EDO/30S MAEVA	250 g/m²	Epoxy polyamide	AQ	53
3	ENDUIT AR 100	1900 g/m²/mm	Epoxy polyamine	SS	
4	LIANT AL8T/AP MAEVA	900 g/m²	Epoxy polyamine	SS	
5	TISSU P45A	450 g/m²	Renfort	SS	
6	LIANT AL8T/AP MAEVA	800 g/m²	Epoxy polyamine	SS	
7	TISSU P45B	450 g/m²	Renfort	SS	
8	LIANT AL8T/AP MAEVA	600 g/m²	Epoxy polyamine	SS	
9	LIANT AL8T/AP MAEVA	562 g/m²	Epoxy polyamine	SS	
10	-=-=-=-=-=-=-=-=-=-=				
11	SILICE F15				
12	DILUANT ED				