Visualize a published system sheet

FNP system

FNP number : 1151

Index FNP : S007

Last publication : 2025/12/03

State : PUBLISHED

Supplier : SPPM

Total thickness : 3,9 mm

public comment EN : March 14th, 2025: Technical datasheet modification in progress. May 20th, 2022: Publication of the Technical Data Sheet for FNP 1151 coating system targeting codification PLK353 - airtightness coating of the extrados of Reactor Building Internal Enclosure (P4-P'4-N4 of PWR French Fleet)

Utilities type : PARC NUCLEAIRE

Codifications published

Série	Groupe
PLK	353

Coat list

Coat number	Product name	Thickness	Nature of the binder	Type of phase	Proportion of solvent
1	ETANPRIM SH	270 µm	Epoxy	SS	
2	STRATILAC ELV2 TAZ		Epoxy	SS	
3	STRATILAC ELV2	2000 µm	Epoxy	SS	
4	ETANPRIM SHV	820 µm	Epoxy	SS	
5	VHM 90	927 g/m²	Renfort		
6	ETANPRIM SHV	360 µm	Epoxy	SS	
7	TM 3000	280 µm	Epoxy	SS	
8	-=-=-=-=-=-=-=-=-=				
9	SILICE 0,1/0,6				
10	SILICE 0,4/0,9				