

Visualize a published system sheet

FNP system

FNP number : 1185

Index FNP : S003

Last publication : 02/12/2025

State : PUBLISHED

Supplier : PPG

Total thickness : 240 µm

public comment EN : 02/12/2025 : Update of technical data sheet for dry extract correction. -- 08/09/2025 : First publication of the coating system FNP1185 for FNP1101 replacement (the paint product Freitapox SR 215 EVO is substituted by Sigmafast 278). !\ Be aware, Sigmafast 278 is categorized CMR product due to oxirane presence in the composition. Reformulation in progress.

intern comment : Le système est publié de manière temporaire. Attente de reformulation de la part de PPG pour sa requalification. Si d'autres PEC sont reformulés et mis à disposition sur le catalogue, alors le FNP1185 devra être dépublié.

Utilities type : PARC NUCLEAIRE

Technical sheet : [FT EN 1185 Ind J.pdf](#)

Codifications published

Série	Groupe
	210
	203
	201
	200

Coat list

Coat number	Product name	Thickness	Nature of the binder	Type of phase	Proportion of solvent
1	SIGMAFAST 278	80 µm	Epoxy polyamidoamine	SV	18.1
2	SIGMAFAST 278	90 µm	Epoxy polyamidoamine	SV	18.1
3	FREITANE 580	70 µm	Polyuréthane acrylique	SV	19
4	-----				
5	DILUANT 21 06				
6	DILUANT 91 92				