Visualize a published system sheet

FNP system

FNP number : 1185

Index FNP : S003

Last publication : 2025/12/02

State : PUBLISHED

Supplier : PPG

Total thickness : 240 µm

public comment EN : 02/12/2025 : Update of technical data sheet for dry extract correction. -- 08/09/2025 : First publication of the coating system FNP1185 for FNP1101 replacement (the paint product Freitapox SR 215 EVO is substituted by Sigmafast 278). /!\ Be aware, Sigmafast 278 is categorized CMR product due to oxirane presence in the composition. Reformulation in progress.

Utilities type : PARC NUCLEAIRE

Technical sheet : FT EN 1185 Ind J.pdf

Codifications published

Série	Groupe
PEA/EEA PEB/EEB PEC/EEC	210
PEA/EEA PEB/EEB PEC/EEC	203
PEA/EEA PEB/EEB PEC/EEC	201
PEA/EEA PEB/EEB PEC/EEC	200

Coat list

Coat number	Product name	Thickness	Nature of the binder	Type of phase	Proportion of solvent
1	SIGMAFAST 278	80 µm	Epoxy polyamidoamine	SV	18.1
2	SIGMAFAST 278	90 µm	Epoxy polyamidoamine	SV	18.1
3	FREITANE 580	70 µm	Polyuréthane acrylique	SV	19
4	-=-=-=-=-=-=-=-=-=-=				
5	DILUANT 21 06				
6	DILUANT 91 92				